

**LP<sup>®</sup> SolidStart<sup>®</sup> I-Joists**  
**Louisiana-Pacific Corporation**

**PR-L238C**

Revised May 27, 2017

Products: LP<sup>®</sup> SolidStart<sup>®</sup> I-Joists (LPI<sup>®</sup> series)  
LP Building Products, Louisiana-Pacific Corporation, 414 Union Street, Suite 2000, Nashville,  
Tennessee 37219  
(615) 986-5600  
[www.lpcorp.com](http://www.lpcorp.com)

1. Basis of the product report:
  - 2015 National Building Code of Canada (NBCC): Clause 1.2.1.1 of Division A and Clauses 4.1, 4.3.1.1, and 9.23.4.2 of Division B
  - CSA O86-14 (Reprinted May 2016) Engineering Design in Wood
  - ASTM D5055-13e1 recognized by CSA O86-14
  - Performance Standard for APA EWS I-Joists, PRI-400
  - Intertek LPI 20, LPI 20X1.7 and LPI 32 Test Report, Intertek LPI 20X1.5 Test Report, PFS LPI 23 (a.k.a. LPI 32) Test Report, APA Reports T2005M-21, T2005M-52, T2006M-03, T2006M-07, T2008P-42, T2008P-45, T2008P-69, T2008P-97, T2008P-111, T2009P-03, T2009P-14, T2009P-21, T2009P-38, T2009P-47, T2009P-60, T2009P-61, T2009P-82, T2010P-36, T2010P-39, T2010P-52A, T2010P-58, T2010P-59, T2011P-08, T2011P-53A, T2012P-25A, T2013P-30, T2013P-38, T2014P-03, T2014P-18, T2014P-29, T2014P-36, T2015P-10, T2016P-16, and T2016P-19, and other qualification data
2. Product description:

LPI 18, 20Plus, 32Plus, 42Plus, and 52Plus series I-joists, as described in Table 1, are made with lumber flanges and oriented strand board (OSB) webs in accordance with the in-plant manufacturing standard approved by APA. LPI 36, 450, 56, and 530 series I-joists, as described in Table 1, are made with laminated veneer lumber (LVL) flanges and OSB webs in accordance with the in-plant manufacturing standard approved by APA.
3. Design properties:

Tables 2 and 3 list the factored resistances for the LP SolidStart I-Joists covered by this report. The maximum spans for LP SolidStart I-Joists shall be in accordance with the recommendations provided by the manufacturer [contact the manufacturer for information or refer to the *Residential Construction Technical Guide*, Lit. Item LPEW0326 or *Light-Frame Commercial, Midrise, and Multifamily Construction Technical Guide*, Lit. Item LPEW0327 ([www.lpcorp.com/resources/literature](http://www.lpcorp.com/resources/literature)) and with APA EWS Standard PRI-400, *Performance Standard for APA EWS I-Joists (Limit States Design)*, Form EWS E720CA ([www.apawood.org/resource-library](http://www.apawood.org/resource-library)), for depths contained in the PRI Series.
4. Product installation:

The LP SolidStart I-Joists covered by this report shall be installed in accordance with the recommendations provided by the manufacturer (see link above) or the APA *I-Joist Construction Details – Canadian Limit States Design – Performance Rated I-Joists in Floor and Roof Framing*, Form E715CA (see link above). Permissible web holes and cantilever reinforcements shall be in accordance with the recommendations provided by the manufacturer or with APA E715CA for products contained in the PRI Series.
5. Fire-rated assemblies:

Fire-rated assemblies shall be constructed in accordance with the recommendations provided by the manufacturer (see link above).

6. Limitations:
- LP SolidStart I-Joists shall be designed in accordance with the code using the design properties specified in this report.
  - LP SolidStart Series I-Joists are limited to dry service conditions as defined in CSA O86, at which the average equilibrium moisture content of solid-sawn lumber over a year is 15 percent or less and does not exceed 19 percent.
  - LP SolidStart I-Joists are produced at Red Bluff, California, Larouche, Quebec, and St. Prime, Quebec under a quality assurance program audited by APA. A list of I-joists manufactured at different LP facilities is documented and audited by APA.
  - This report is subject to re-examination in one year.

7. Identification:  
 The LP SolidStart I-Joists described in this report are identified by a label bearing the manufacturer's name (Louisiana-Pacific Corporation or Abitibi – LP Engineered Wood Inc.) and/or trademark, the APA assigned plant number (1069 for the Red Bluff plant, 1068 for the Larouche plant, and 1077 for the St. Prime plant), the I-joist series designation and depth, the APA logo, the report number PR-L238, and a means of identifying the date of manufacture.

Table 1. Description of LP SolidStart I-Joists<sup>(a)</sup>

Joist Series	Joist Depths, mm (in.)	Flanges			Web	
		Material	Dimension		Material	Thickness <sup>(b)</sup> , mm (in.)
			Depth, mm (in.)	Width, mm (in.)		
LPI 18	200 – 406 (7-7/8 – 16)	Proprietary SPF	38 (1-1/2)	64 (2-1/2)	OSB	9.5 (3/8)
LPI 20Plus	200 – 406 (7-7/8 – 16)	Proprietary SPF	38 (1-1/2)	64 (2-1/2)	OSB	9.5 (3/8)
LPI 32Plus	200 – 406 (7-7/8 – 16)	MSR SPF	38 (1-1/2)	64 (2-1/2)	OSB	9.5 (3/8)
LPI 42Plus	200 – 610 (7-7/8 – 24)	Proprietary SPF	38 (1-1/2)	89 (3-1/2)	OSB	9.5 <sup>(c)</sup> (3/8)
LPI 52Plus	235 – 610 (9-1/4 – 24)	MSR SPF	38 (1-1/2)	89 (3-1/2)	OSB	11 (7/16)
LPI 36	302 – 610 (11-7/8 – 24)	LVL	38 (1-1/2)	57 (2-1/4)	OSB	9.5 (3/8)
LPI 56	302 – 610 (11-7/8 – 24)	LVL	38 (1-1/2)	89 (3-1/2)	OSB	11 (7/16)
LPI 450	241 – 406 (9-1/2 – 16)	LVL	33 (1-5/16)	45 (1-3/4)	OSB	9.5 (3/8)
LPI 530	241 – 406 (9-1/2 – 16)	LVL	33 (1-5/16)	53 (2-1/16)	OSB	9.5 (3/8)

<sup>(a)</sup> Referenced dimensions are nominal. Tolerances are as specified in the in-plant quality manual.

<sup>(b)</sup> 11-mm (7/16-inch) webs shall be permitted to substitute for 9.5-mm (3/8-inch) webs.

<sup>(c)</sup> 11-mm (7/16-inch) webs for joist depths exceeding 406 mm (16 inches).

Table 2. Factored Resistances and Stiffnesses for LP SolidStart I-Joists<sup>(a)</sup>

Joist Series Designation	Joist Depth, mm (in.)	EI, <sup>(b)</sup> 10 <sup>6</sup> kN-mm <sup>2</sup> (10 <sup>6</sup> lbf-in. <sup>2</sup> )	M <sub>r</sub> , <sup>(c)</sup> kN-mm (lbf-ft)	V <sub>r</sub> , <sup>(d)</sup> kN (lbf)	VLC <sub>r</sub> , <sup>(e)</sup> kN/m (plf)	K, <sup>(f)</sup> kN (10 <sup>6</sup> lbf)
LPI 18	200 (7-7/8)	198 (69)	4,307 (3,175)	6.60 (1,485)	46.3 (3,170)	16,120 (3.62)
	225 (8-7/8)	264 (92)	4,972 (3,665)	7.41 (1,665)	46.3 (3,170)	17,828 (4.01)
	235 (9-1/4)	327 (114)	5,220 (3,850)	7.72 (1,735)	46.3 (3,170)	18,521 (4.16)
	241 (9-1/2)	407 (142)	5,333 (3,935)	7.93 (1,785)	46.3 (3,170)	18,948 (4.26)
	286 (11-1/4)	654 (228)	6,573 (4,850)	8.99 (2,020)	42.8 (2,935)	22,098 (4.97)
	302 (11-7/8)	712 (248)	6,990 (5,155)	9.37 (2,105)	42.8 (2,935)	23,219 (5.22)
	356 (14)	1,065 (371)	8,388 (6,185)	10.60 (2,385)	38.9 (2,670)	27,115 (6.10)
406 (16)	1,475 (514)	9,539 (7,035)	11.79 (2,650)	29.2 (2,000)	30,798 (6.92)	
LPI 20Plus	200 (7-7/8)	336 (117)	5,040 (3,715)	7.34 (1,650)	46.3 (3,170)	16,280 (3.66)
	225 (8-7/8)	451 (157)	5,818 (4,290)	8.25 (1,855)	46.3 (3,170)	17,988 (4.04)
	235 (9-1/4)	496 (173)	6,111 (4,505)	8.60 (1,935)	46.3 (3,170)	18,682 (4.20)
	240	525 (183)	6,303 (4,650)	8.78 (1,975)	46.3 (3,170)	19,002 (4.27)
	241 (9-1/2)	531 (185)	6,336 (4,675)	8.85 (1,990)	46.3 (3,170)	19,109 (4.30)
	286 (11-1/4)	804 (280)	7,689 (5,670)	10.00 (2,250)	42.8 (2,935)	22,258 (5.00)
	300	901 (314)	8,422 (6,210)	10.36 (2,330)	42.8 (2,935)	23,272 (5.23)
	302 (11-7/8)	913 (318)	8,467 (6,245)	10.43 (2,345)	42.8 (2,935)	23,379 (5.26)
	356 (14)	1,360 (474)	9,922 (7,320)	11.79 (2,650)	38.9 (2,670)	27,329 (6.14)
	360	1,400 (488)	10,057 (7,420)	11.94 (2,685)	36.5 (2,500)	27,649 (6.22)
	400	1,805 (629)	11,196 (8,260)	12.95 (2,910)	36.5 (2,500)	30,584 (6.88)
	406 (16)	1,871 (652)	11,388 (8,400)	13.13 (2,950)	36.5 (2,500)	31,065 (6.98)
LPI 32Plus	200 (7-7/8)	405 (141)	6,517 (4,805)	7.34 (1,650)	53.6 (3,670)	16,280 (3.66)
	225 (8-7/8)	531 (185)	7,532 (5,555)	8.25 (1,855)	53.6 (3,670)	17,988 (4.04)
	235 (9-1/4)	594 (207)	7,915 (5,840)	8.60 (1,935)	53.6 (3,670)	18,682 (4.20)
	241 (9-1/2)	634 (221)	8,163 (6,020)	8.85 (1,990)	53.6 (3,670)	19,109 (4.30)
	286 (11-1/4)	950 (331)	9,944 (7,335)	10.00 (2,250)	53.6 (3,670)	22,258 (5.00)
	302 (11-7/8)	1,076 (375)	10,576 (7,800)	10.43 (2,345)	53.6 (3,670)	23,379 (5.26)
	356 (14)	1,575 (549)	12,729 (9,390)	11.79 (2,650)	38.9 (2,670)	27,329 (6.14)
	406 (16)	2,132 (743)	14,759 (10,885)	13.13 (2,950)	36.5 (2,500)	31,065 (6.98)
LPI 42Plus	200 (7-7/8)	585 (204)	9,674 (7,135)	8.04 (1,805)	53.6 (3,670)	18,201 (4.09)
	225 (8-7/8)	781 (272)	11,173 (8,240)	8.88 (1,995)	53.6 (3,670)	20,550 (4.62)
	235 (9-1/4)	864 (301)	11,748 (8,665)	9.20 (2,070)	53.6 (3,670)	21,404 (4.81)
	240	910 (317)	12,042 (8,880)	9.37 (2,105)	53.6 (3,670)	21,884 (4.92)
	241 (9-1/2)	921 (321)	12,120 (8,940)	9.41 (2,115)	53.6 (3,670)	21,991 (4.94)
	286 (11-1/4)	1,377 (480)	14,770 (10,895)	10.88 (2,445)	53.6 (3,670)	26,047 (5.86)
	300	1,535 (535)	15,604 (11,510)	11.34 (2,550)	53.6 (3,670)	27,382 (6.16)
	302 <sup>(g)</sup> (11-7/8)	1,570 (547)	15,706 (11,585)	11.41 (2,565)	53.6 (3,670)	27,489 (6.18)
	356 <sup>(g)</sup> (14)	2,301 (802)	18,919 (13,955)	13.16 (2,960)	48.7 (3,335)	32,399 (7.28)
	360	2,368 (825)	19,178 (14,145)	13.30 (2,990)	48.7 (3,335)	32,773 (7.37)
	400	3,025 (1,054)	21,557 (15,900)	14.64 (3,290)	48.7 (3,335)	36,402 (8.18)
	406 <sup>(g)</sup> (16)	3,134 (1,092)	21,930 (16,175)	14.85 (3,340)	48.7 (3,335)	36,990 (8.32)
	457 (18)	3,825 (1,333)	24,805 (18,295)	17.94 (4,035)	41.4 (2,835)	51,241 (11.52)
	508 (20)	4,844 (1,688)	27,443 (20,240)	19.62 (4,410)	38.5 (2,635)	56,952 (12.80)
	559 (22)	5,992 (2,088)	30,070 (22,180)	21.27 (4,785)	31.6 (2,170)	62,610 (14.08)
	610 (24)	7,272 (2,534)	32,652 (24,085)	22.96 (5,160)	26.8 (1,835)	68,321 (15.36)

(Footnotes on Page 4)

Table 2. Factored Resistances and Sifnesses for LP SolidStart I-Joists<sup>(a)</sup> (Continued)

Joist Series Designation	Joist Depth (inches, unless otherwise noted)	EI, <sup>(b)</sup> 10 <sup>6</sup> kN-mm <sup>2</sup> (10 <sup>6</sup> lbf-in. <sup>2</sup> )	M <sub>r</sub> , <sup>(c)</sup> kN-mm (lbf-ft)	V <sub>r</sub> , <sup>(d)</sup> kN (lbf)	VLC <sub>r</sub> , <sup>(e)</sup> kN/m (plf)	K, <sup>(f)</sup> kN (10 <sup>6</sup> lbf)
LPI 52Plus	235 (9-1/4)	958 (334)	14,296 (10,545)	12.04 (2,705)	58.4 (4,005)	26,314 (5.92)
	241 (9-1/2)	1,022 (356)	14,747 (10,875)	12.25 (2,755)	58.4 (4,005)	27,062 (6.08)
	286 (11-1/4)	1,518 (529)	17,961 (13,245)	13.87 (3,115)	58.4 (4,005)	32,026 (7.20)
	302 (11-7/8)	1,722 (600)	19,111 (14,095)	14.43 (3,245)	58.4 (4,005)	33,787 (7.60)
	356 (14)	2,508 (874)	23,012 (16,975)	16.36 (3,680)	53.6 (3,670)	39,872 (8.96)
	406 (16)	3,395 (1,183)	26,688 (19,685)	18.15 (4,080)	46.3 (3,170)	45,530 (10.24)
	457 (18)	4,419 (1,540)	30,171 (22,255)	19.97 (4,490)	41.4 (2,835)	51,241 (11.52)
	508 (20)	5,590 (1,948)	33,396 (24,630)	21.80 (4,900)	38.5 (2,635)	56,952 (12.80)
	559 (22)	6,910 (2,408)	36,576 (26,975)	23.59 (5,305)	31.6 (2,170)	62,610 (14.08)
610 (24)	8,377 (2,919)	39,721 (29,295)	25.42 (5,715)	26.8 (1,835)	68,321 (15.36)	
LPI 36	302 (11-7/8)	1,231 (429)	14,533 (10,720)	11.34 (2,550)	43.8 (3,000)	24,980 (5.62)
	356 (14)	1,785 (622)	17,487 (12,900)	12.85 (2,890)	43.8 (3,000)	29,357 (6.60)
	406 (16)	2,399 (836)	20,283 (14,960)	14.18 (3,190)	43.8 (3,000)	33,360 (7.50)
	457 (18)	3,105 (1,082)	22,854 (16,855)	15.34 (3,450)	31.6 (2,170)	37,363 (8.40)
	508 (20)	3,903 (1,360)	25,413 (18,745)	16.29 (3,660)	31.6 (2,170)	41,313 (9.29)
	559 (22)	4,790 (1,669)	27,939 (20,605)	17.10 (3,845)	29.2 (2,000)	45,370 (10.20)
	610 (24)	5,768 (2,010)	30,453 (22,460)	17.73 (3,985)	26.8 (1,835)	49,213 (11.06)
LPI 56	302 (11-7/8)	1,917 (668)	22,933 (16,915)	14.43 (3,245)	58.4 (4,005)	29,303 (6.59)
	356 (14)	2,778 (968)	27,623 (20,375)	16.36 (3,680)	53.6 (3,670)	34,214 (7.69)
	406 (16)	3,733 (1,301)	32,032 (23,625)	18.15 (4,080)	46.3 (3,170)	38,911 (8.75)
	457 (18)	4,833 (1,684)	36,102 (26,630)	19.97 (4,490)	41.4 (2,835)	43,608 (9.80)
	508 (20)	6,069 (2,115)	40,138 (29,605)	21.80 (4,900)	38.5 (2,635)	48,305 (10.86)
	559 (22)	7,453 (2,597)	44,141 (32,555)	23.59 (5,305)	31.6 (2,170)	53,002 (11.92)
	610 (24)	8,974 (3,127)	48,121 (35,495)	25.42 (5,715)	26.8 (1,835)	57,699 (12.97)
LPI 450	241 (9-1/2)	488 (170)	7,554 (5,570)	8.64 (1,940)	48.7 (3,335)	25,247 (5.68)
	302 (11-7/8)	821 (286)	9,741 (7,185)	10.04 (2,255)	48.7 (3,335)	31,225 (7.02)
	356 (14)	1,202 (419)	11,545 (8,515)	11.27 (2,535)	26.8 (1,835)	36,616 (8.23)
	406 (16)	1,633 (569)	13,214 (9,745)	12.46 (2,800)	26.8 (1,835)	41,740 (9.38)
LPI 530	241 (9-1/2)	574 (200)	9,020 (6,655)	9.41 (2,115)	48.7 (3,335)	25,514 (5.74)
	302 (11-7/8)	967 (337)	11,613 (8,565)	10.99 (2,470)	48.7 (3,335)	31,545 (7.09)
	356 (14)	1,412 (492)	13,778 (10,160)	12.39 (2,785)	26.8 (1,835)	36,990 (8.32)
	406 (16)	1,911 (666)	15,762 (11,625)	13.73 (3,085)	26.8 (1,835)	42,114 (9.47)

For Imperial: 1 mm = 0.0394 in., 1 N = 0.2248 lbf, 1 kN/m = 5.71 lbf/in.

- (a) All factored resistance values include the resistance factor specified in CSA-O86. The tabulated values are for the standard term of load duration (K<sub>D</sub> = 1.0). All values, except for EI, VLC<sub>r</sub>, and K, shall be adjusted for other load durations in accordance with the code.
- (b) Bending stiffness (EI) of the I-joist
- (c) Factored moment resistance (M<sub>r</sub>) of the I-joist, which shall not be increased by any system factor (K<sub>H</sub> = 1.0).
- (d) Factored shear resistance (V<sub>r</sub>) of the I-joist.
- (e) Factored uniform vertical load resistance (VLC<sub>r</sub>) of the I-joist.
- (f) Coefficient of shear deflection (K). For calculating uniform load and center-point load deflections of the I-joist in a simple-span application, use Equations 1 and 2.

$$\text{Uniform Load: } \delta = \frac{5\omega\ell^4}{384EI} + \frac{\omega\ell^2}{K} \quad [1]$$

$$\text{Center-Point Load: } \delta = \frac{P\ell^3}{48EI} + \frac{2P\ell}{K} \quad [2]$$

Where:  $\delta$  = calculated deflection, mm (in.),  
 $\omega$  = uniform load, kN/mm (lbf/in.),  
 $\ell$  = design span, mm (in.),  
P = concentrated load, kN (lbf),  
EI = bending stiffness of the I-joist, kN-mm<sup>2</sup> (lbf-in.<sup>2</sup>), and  
K = coefficient of shear deflection, kN (lbf).

<sup>(9)</sup> Also recognized as PRI-80 series I-joists.

Table 3. Factored Reaction Resistances for LP SolidStart I-Joists<sup>(a,b,c,d)</sup> and Specified Compressive Strength Perpendicular to Grain for Flanges

Joist Series Designation	Joist Depth, mm (in.)	Intermediate Reaction <sup>(e)</sup> , kN (lbf)				End Reaction <sup>(f)</sup> kN (lbf)				Specified Compressive Strength Perpendicular to Grain ( $f_{cp}$ ), MPa (psi)
		89 mm (3-1/2 in.) Brg. Length		140 mm (5-1/2 in.) Brg. Length		38 mm (1-1/2 in.) Brg. Length		102 mm (4 in.) Brg. Length		
		With Brg. Stiffeners		With Brg. Stiffeners		With Brg. Stiffeners		With Brg. Stiffeners		
		No	Yes	No	Yes	No	Yes	No	Yes	
LPI 18	200 (7-7/8)	13.27 (2,985)	14.29 (3,210)	14.85 (3,340)	15.80 (3,550)	6.11 (1,375)	6.60 (1,485)	6.60 (1,485)	6.60 (1,485)	5.3 (769)
	225 (8-7/8)	13.62 (3,060)	14.71 (3,305)	15.20 (3,415)	16.29 (3,660)	6.11 (1,375)	6.95 (1,565)	6.85 (1,540)	7.41 (1,665)	
	235 (9-1/4)	13.76 (3,095)	14.85 (3,340)	15.38 (3,455)	16.50 (3,710)	6.11 (1,375)	7.09 (1,595)	6.95 (1,565)	7.72 (1,735)	
	241 (9-1/2)	13.87 (3,115)	14.99 (3,370)	15.48 (3,480)	16.64 (3,740)	6.11 (1,375)	7.20 (1,620)	6.99 (1,570)	7.93 (1,785)	
	286 (11-1/4)	14.50 (3,260)	15.69 (3,530)	16.15 (3,630)	17.55 (3,945)	6.11 (1,375)	7.79 (1,750)	7.23 (1,625)	8.99 (2,020)	
	302 (11-7/8)	14.71 (3,305)	15.94 (3,585)	16.39 (3,685)	17.87 (4,015)	6.11 (1,375)	8.04 (1,805)	7.30 (1,640)	9.37 (2,105)	
	356 (14)	15.48 (3,480)	16.81 (3,780)	17.20 (3,865)	18.96 (4,260)	6.11 (1,375)	8.81 (1,980)	7.58 (1,705)	10.60 (2,385)	
406 (16)	16.22 (3,645)	17.66 (3,970)	18.01 (4,050)	20.04 (4,505)	6.11 (1,375)	9.51 (2,140)	7.83 (1,760)	11.79 (2,650)		
LPI 20Plus	200 (7-7/8)	14.74 (3,315)	15.90 (3,575)	16.50 (3,710)	17.55 (3,945)	6.81 (1,530)	7.34 (1,650)	7.34 (1,650)	7.34 (1,650)	5.3 (769)
	225 (8-7/8)	15.16 (3,410)	16.36 (3,680)	16.92 (3,805)	18.11 (4,070)	6.81 (1,530)	7.72 (1,735)	7.62 (1,715)	8.25 (1,855)	
	235 (9-1/4)	15.31 (3,440)	16.53 (3,715)	17.10 (3,845)	18.36 (4,130)	6.81 (1,530)	7.90 (1,775)	7.72 (1,735)	8.60 (1,935)	
	240	15.38 (3,455)	16.64 (3,740)	17.17 (3,860)	18.46 (4,150)	6.81 (1,530)	7.97 (1,790)	7.76 (1,745)	8.78 (1,975)	
	241 (9-1/2)	15.41 (3,465)	16.67 (3,750)	17.20 (3,865)	18.50 (4,160)	6.81 (1,530)	8.00 (1,800)	7.79 (1,750)	8.85 (1,990)	
	286 (11-1/4)	16.11 (3,620)	17.45 (3,920)	17.97 (4,040)	19.52 (4,390)	6.81 (1,530)	8.67 (1,950)	8.04 (1,805)	10.00 (2,250)	
	300	16.32 (3,670)	17.69 (3,980)	18.18 (4,090)	19.83 (4,460)	6.81 (1,530)	8.92 (2,005)	8.11 (1,825)	10.36 (2,330)	
	302 (11-7/8)	16.36 (3,680)	17.73 (3,985)	18.22 (4,095)	19.87 (4,465)	6.81 (1,530)	8.95 (2,010)	8.14 (1,830)	10.43 (2,345)	
	356 (14)	17.24 (3,875)	18.71 (4,205)	19.13 (4,300)	21.10 (4,745)	6.81 (1,530)	9.79 (2,200)	8.42 (1,895)	11.79 (2,650)	
	360	17.31 (3,890)	18.78 (4,220)	19.24 (4,325)	21.20 (4,765)	6.81 (1,530)	9.86 (2,220)	8.46 (1,900)	11.94 (2,685)	
	400	17.94 (4,035)	19.52 (4,390)	19.90 (4,475)	22.12 (4,970)	6.81 (1,530)	10.50 (2,360)	8.67 (1,950)	12.95 (2,910)	
406 (16)	18.04 (4,055)	19.62 (4,410)	20.01 (4,500)	22.29 (5,010)	6.81 (1,530)	10.60 (2,385)	8.71 (1,955)	13.13 (2,950)		
LPI 32Plus	200 (7-7/8)	14.74 (3,315)	15.90 (3,575)	16.50 (3,710)	17.55 (3,945)	6.81 (1,530)	7.34 (1,650)	7.34 (1,650)	7.34 (1,650)	6.5 (943)
	225 (8-7/8)	15.16 (3,410)	16.36 (3,680)	16.92 (3,805)	18.11 (4,070)	6.81 (1,530)	7.72 (1,735)	7.62 (1,715)	8.25 (1,855)	
	235 (9-1/4)	15.31 (3,440)	16.53 (3,715)	17.10 (3,845)	18.36 (4,130)	6.81 (1,530)	7.90 (1,775)	7.72 (1,735)	8.60 (1,935)	
	241 (9-1/2)	15.41 (3,465)	16.67 (3,750)	17.20 (3,865)	18.50 (4,160)	6.81 (1,530)	8.00 (1,800)	7.79 (1,750)	8.85 (1,990)	
	286 (11-1/4)	16.11 (3,620)	17.45 (3,920)	17.97 (4,040)	19.52 (4,390)	6.81 (1,530)	8.67 (1,950)	8.04 (1,805)	10.00 (2,250)	
	302 (11-7/8)	16.36 (3,680)	17.73 (3,985)	18.22 (4,095)	19.87 (4,465)	6.81 (1,530)	8.95 (2,010)	8.14 (1,830)	10.43 (2,345)	
	356 (14)	17.24 (3,875)	18.71 (4,205)	19.13 (4,300)	21.10 (4,745)	6.81 (1,530)	9.79 (2,200)	8.42 (1,895)	11.79 (2,650)	
406 (16)	18.04 (4,055)	19.62 (4,410)	20.01 (4,500)	22.29 (5,010)	6.81 (1,530)	10.60 (2,385)	8.71 (1,955)	13.13 (2,950)		

(Footnotes on Page 8)

Table 3. Factored Reaction Resistances for LP SolidStart I-Joists<sup>(a,b,c,d)</sup> and Specified Compressive Strength Perpendicular to Grain for Flanges  
 (Continued)

Joist Series Designation	Joist Depth, mm (in.)	Intermediate Reaction <sup>(e)</sup> , kN (lbf)				End Reaction <sup>(f)</sup> , kN (lbf)				Specified Compressive Strength Perpendicular to Grain ( $f_{cp}$ ), MPa (psi)
		89 mm (3-1/2 in.) Brg. Length		140 mm (5-1/2 in.) Brg. Length		38 mm (1-1/2 in.) Brg. Length		102 mm (4 in.) Brg. Length		
		With Brg. Stiffeners		With Brg. Stiffeners		With Brg. Stiffeners		With Brg. Stiffeners		
		No	Yes	No	Yes	No	Yes	No	Yes	
LPI 42Plus	200 (7-7/8)	19.76 (4,445)	20.50 (4,610)	19.76 (4,445)	20.85 (4,690)	8.04 (1,805)	8.04 (1,805)	8.04 (1,805)	8.04 (1,805)	6.5 (943)
	225 (8-7/8)	20.15 (4,530)	21.24 (4,775)	20.29 (4,560)	21.80 (4,900)	8.21 (1,845)	8.88 (1,995)	8.71 (1,955)	8.88 (1,995)	
	235 (9-1/4)	20.29 (4,560)	21.52 (4,840)	20.50 (4,610)	22.19 (4,990)	8.28 (1,865)	9.20 (2,070)	8.99 (2,020)	9.20 (2,070)	
	240	20.33 (4,570)	21.66 (4,870)	20.61 (4,635)	22.36 (5,025)	8.32 (1,870)	9.37 (2,105)	9.09 (2,045)	9.37 (2,105)	
	241 (9-1/2)	20.36 (4,575)	21.73 (4,885)	20.64 (4,640)	22.43 (5,045)	8.32 (1,870)	9.41 (2,115)	9.16 (2,060)	9.41 (2,115)	
	286 (11-1/4)	21.03 (4,725)	22.96 (5,160)	21.59 (4,855)	24.08 (5,415)	8.64 (1,940)	10.29 (2,310)	10.64 (2,390)	10.88 (2,445)	
	300	21.20 (4,765)	23.41 (5,265)	21.87 (4,915)	24.61 (5,530)	8.74 (1,965)	10.57 (2,375)	11.13 (2,500)	11.34 (2,550)	
	302 <sup>(g)</sup> (11-7/8)	21.24 (4,775)	23.45 (5,270)	21.90 (4,925)	24.68 (5,550)	8.74 (1,965)	10.60 (2,385)	11.20 (2,520)	11.41 (2,565)	
	356 <sup>(g)</sup> (14)	22.05 (4,955)	25.03 (5,625)	23.03 (5,175)	26.71 (6,005)	9.13 (2,050)	11.65 (2,620)	11.20 (2,520)	13.16 (2,960)	
	360	22.12 (4,970)	25.13 (5,650)	23.13 (5,200)	26.89 (6,045)	9.16 (2,060)	11.72 (2,635)	11.20 (2,520)	13.30 (2,990)	
	400	22.68 (5,100)	26.33 (5,920)	23.98 (5,390)	28.40 (6,385)	9.44 (2,125)	12.50 (2,810)	11.20 (2,520)	14.64 (3,290)	
	406 <sup>(g)</sup> (16)	22.78 (5,120)	26.50 (5,960)	24.12 (5,420)	28.64 (6,440)	9.48 (2,130)	12.64 (2,840)	11.20 (2,520)	14.85 (3,340)	
	457 (18)	24.22 (5,445)	30.08 (6,765)	27.03 (6,075)	32.47 (7,300)	10.53 <sup>(h)</sup> (2,370) <sup>(h)</sup>	16.18 <sup>(h)</sup> (3,640) <sup>(h)</sup>	11.87 (2,670)	17.94 (4,035)	
	508 (20)	24.22 (5,445)	30.96 (6,960)	27.03 (6,075)	33.95 (7,630)	10.53 <sup>(h)</sup> (2,370) <sup>(h)</sup>	17.20 <sup>(h)</sup> (3,865) <sup>(h)</sup>	11.87 (2,670)	19.62 (4,410)	
559 (22)	24.22 (5,445)	31.80 (7,150)	27.03 (6,075)	35.31 (7,940)	10.53 <sup>(h)</sup> (2,370) <sup>(h)</sup>	18.22 <sup>(h)</sup> (4,095) <sup>(h)</sup>	11.87 (2,670)	21.27 (4,785)		
610 (24)	24.22 (5,445)	32.58 (7,325)	27.03 (6,075)	36.58 (8,225)	10.53 <sup>(h)</sup> (2,370) <sup>(h)</sup>	18.99 <sup>(h)</sup> (4,270) <sup>(h)</sup>	11.87 (2,670)	22.96 (5,160)		
LPI 52Plus	235 (9-1/4)	23.87 (5,365)	25.84 (5,810)	24.57 (5,525)	26.68 (6,000)	9.34 (2,100)	11.44 (2,575)	11.16 (2,510)	12.04 (2,705)	6.5 (943)
	241 (9-1/2)	23.87 (5,365)	26.05 (5,855)	24.68 (5,550)	26.96 (6,060)	9.37 (2,105)	11.58 (2,605)	11.23 (2,525)	12.25 (2,755)	
	286 (11-1/4)	23.98 (5,390)	27.56 (6,195)	25.31 (5,690)	28.86 (6,485)	9.55 (2,145)	12.46 (2,800)	11.69 (2,630)	13.87 (3,115)	
	302 (11-7/8)	24.01 (5,400)	28.08 (6,315)	25.52 (5,740)	29.56 (6,645)	9.62 (2,160)	12.78 (2,875)	11.87 (2,670)	14.43 (3,245)	
	356 (14)	24.12 (5,420)	29.91 (6,725)	26.29 (5,910)	31.87 (7,165)	9.72 (2,185)	13.83 (3,110)	12.95 (2,910)	16.36 (3,680)	
	406 (16)	24.22 (5,445)	31.63 (7,110)	27.03 (6,075)	34.09 (7,665)	9.83 (2,210)	14.81 (3,330)	13.94 (3,135)	18.15 (4,080)	
	457 (18)	24.22 (5,445)	33.35 (7,495)	27.03 (6,075)	36.26 (8,155)	11.94 <sup>(h)</sup> (2,685) <sup>(h)</sup>	17.48 <sup>(h)</sup> (3,930) <sup>(h)</sup>	14.95 (3,360)	19.97 (4,490)	
	508 (20)	24.22 (5,445)	35.03 (7,875)	27.03 (6,075)	38.44 (8,640)	11.94 <sup>(h)</sup> (2,685) <sup>(h)</sup>	18.78 <sup>(h)</sup> (4,220) <sup>(h)</sup>	14.95 (3,360)	21.80 (4,900)	
LPI 36	302 (11-7/8)	17.55 (3,945)	21.80 (4,900)	19.90 (4,475)	24.36 (5,475)	7.20 (1,620)	10.53 (2,370)	9.06 (2,035)	11.34 (2,550)	6.90 (1,001)
	356 (14)	17.55 (3,945)	22.50 (5,060)	19.90 (4,475)	25.03 (5,625)	7.20 (1,620)	10.64 (2,390)	9.30 (2,090)	12.85 (2,890)	
	406 (16)	17.55 (3,945)	23.20 (5,215)	19.90 (4,475)	25.66 (5,770)	7.20 (1,620)	10.71 (2,405)	9.55 (2,145)	14.18 (3,190)	
	457 (18)	17.55 (3,945)	23.91 (5,375)	19.90 (4,475)	26.33 (5,920)	8.25 <sup>(h)</sup> (1,855) <sup>(h)</sup>	12.64 <sup>(h)</sup> (2,840) <sup>(h)</sup>	9.79 (2,200)	15.34 (3,450)	
	508 (20)	17.55 (3,945)	24.57 (5,525)	19.90 (4,475)	26.96 (6,060)	8.32 <sup>(h)</sup> (1,870) <sup>(h)</sup>	13.06 <sup>(h)</sup> (2,935) <sup>(h)</sup>	10.04 (2,255)	16.29 (3,660)	
	559 (22)	17.55 (3,945)	25.27 (5,680)	19.90 (4,475)	27.59 (6,205)	8.42 <sup>(h)</sup> (1,895) <sup>(h)</sup>	13.44 <sup>(h)</sup> (3,025) <sup>(h)</sup>	10.29 (2,310)	17.10 (3,845)	
610 (24)	17.55 (3,945)	25.98 (5,840)	19.90 (4,475)	28.26 (6,355)	8.53 <sup>(h)</sup> (1,920) <sup>(h)</sup>	13.76 <sup>(h)</sup> (3,095) <sup>(h)</sup>	10.53 (2,370)	17.73 (3,985)		

(Footnotes on Page 8)

Table 3. Factored Reaction Resistances for LP SolidStart I-Joists<sup>(a,b,c,d)</sup> and Specified Compressive Strength Perpendicular to Grain for Flanges  
 (Continued)

Joist Series Designation	Joist Depth, mm (in.)	Intermediate Reaction <sup>(e)</sup> , kN (lbf)				End Reaction <sup>(f)</sup> , kN (lbf)				Specified Compressive Strength Perpendicular to Grain ( $f_{cp}$ ), MPa (psi)
		89 mm (3-1/2 in.) Brg. Length		140 mm (5-1/2 in.) Brg. Length		38 mm (1-1/2 in.) Brg. Length		102 mm (4 in.) Brg. Length		
		With Brg. Stiffeners		With Brg. Stiffeners		With Brg. Stiffeners		With Brg. Stiffeners		
		No	Yes	No	Yes	No	Yes	No	Yes	
LPI 56	302 (11-7/8)	21.98 (4,940)	27.10 (6,095)	25.77 (5,795)	28.50 (6,410)	8.04 (1,805)	11.65 (2,620)	10.64 (2,390)	14.43 (3,245)	6.90 (1,001)
	356 (14)	21.98 (4,940)	28.47 (6,400)	25.77 (5,795)	30.19 (6,785)	8.04 (1,805)	12.32 (2,770)	10.78 (2,425)	16.36 (3,680)	
	406 (16)	21.98 (4,940)	29.80 (6,700)	25.77 (5,795)	31.77 (7,140)	8.04 (1,805)	12.95 (2,910)	10.92 (2,455)	18.15 (4,080)	
	457 (18)	21.98 (4,940)	31.14 (7,000)	25.77 (5,795)	33.35 (7,495)	9.23 <sup>(h)</sup> (2,075) <sup>(h)</sup>	16.15 <sup>(h)</sup> (3,630) <sup>(h)</sup>	11.06 (2,485)	19.97 (4,490)	
	508 (20)	21.98 (4,940)	32.44 (7,290)	25.77 (5,795)	34.93 (7,855)	9.30 <sup>(h)</sup> (2,090) <sup>(h)</sup>	17.24 <sup>(h)</sup> (3,875) <sup>(h)</sup>	11.20 (2,520)	21.80 (4,900)	
	559 (22)	21.98 (4,940)	33.77 (7,590)	25.77 (5,795)	36.51 (8,210)	9.37 <sup>(h)</sup> (2,105) <sup>(h)</sup>	18.32 <sup>(h)</sup> (4,120) <sup>(h)</sup>	11.34 (2,550)	23.59 (5,305)	
610 (24)	21.98 (4,940)	35.10 (7,890)	25.77 (5,795)	38.12 (8,570)	9.41 <sup>(h)</sup> (2,115) <sup>(h)</sup>	19.45 <sup>(h)</sup> (4,370) <sup>(h)</sup>	11.48 (2,580)	25.42 (5,715)		
LPI 450	241 (9-1/2)	13.02 (2,930)	14.64 (3,290)	15.41 (3,465)	16.96 (3,810)	5.90 (1,325)	7.72 (1,735)	7.30 (1,640)	8.64 (1,940)	6.90 (1,001)
	302 (11-7/8)	13.48 (3,030)	15.66 (3,520)	15.83 (3,560)	17.62 (3,960)	5.90 (1,325)	8.50 (1,910)	7.51 (1,690)	10.04 (2,255)	
	356 (14)	13.94 (3,135)	16.57 (3,725)	16.18 (3,640)	18.22 (4,095)	5.90 (1,325)	9.16 (2,060)	7.72 (1,735)	11.27 (2,535)	
	406 (16)	14.36 (3,230)	17.45 (3,920)	16.57 (3,725)	18.82 (4,230)	5.90 (1,325)	9.79 (2,200)	7.90 (1,775)	12.46 (2,800)	
LPI 530	241 (9-1/2)	14.50 (3,260)	16.15 (3,630)	15.90 (3,575)	17.55 (3,945)	6.18 (1,390)	7.90 (1,775)	7.69 (1,730)	9.41 (2,115)	6.90 (1,001)
	302 (11-7/8)	14.88 (3,345)	17.45 (3,920)	16.85 (3,790)	19.20 (4,315)	6.18 (1,390)	8.74 (1,965)	7.86 (1,770)	10.99 (2,470)	
	356 (14)	15.20 (3,415)	18.64 (4,190)	17.73 (3,985)	20.68 (4,650)	6.18 (1,390)	9.48 (2,130)	8.04 (1,805)	12.39 (2,785)	
	406 (16)	15.52 (3,490)	19.73 (4,435)	18.53 (4,165)	22.05 (4,955)	6.18 (1,390)	10.18 (2,290)	8.18 (1,840)	13.73 (3,085)	

For Imperial: 1 mm = 0.0394 in., 1 N = 0.2248 lbf, 1 MPa = 145.04 psi

- (a) Reaction capacity shall be limited by the tabulated I-joist reaction capacity, flange bearing capacity or the bearing capacity of the support material, whichever is less. The flange bearing capacity is based on the specified compressive strength perpendicular to grain of the I-joist flange, the net flange width and the bearing length, and may be further limited by the bearing capacity of the support material. To calculate the net flange width, subtract 6.4 mm (0.25 inch) from the flange width (see Table 1) of the LPI 18, LPI 20Plus, LPI 32Plus, LPI 42Plus, and LPI 52Plus series I-joists, or subtract 2.5 mm (0.10 inch) from the flange width (see Table 1) of the LPI 36, LPI 56, LPI 450, and LPI 530 series I-joists.
- (b) The tabulated values are for the standard term of load duration ( $K_D = 1.0$ ).
- (c) Interpolation between bearing lengths is permitted.
- (d) Bearing stiffeners shall be installed in accordance with the recommendations provided by the manufacturer.
- (e) For all depths of 241 mm (9-1/2 inches) and greater, the intermediate reaction with a minimum bearing length of 76 mm (3 inches) shall be permitted to be determined based on the intermediate reaction values with a bearing length of 89 mm (3-1/2 inches) and 140 mm (5-1/2 inches).
- (f) The minimum bearing length for end reactions is 38 mm (1-1/2 inches), unless otherwise noted.
- (g) Also recognized as PRI-80 series I-joists.
- (h) Minimum bearing length is 64 mm (2-1/2 inches).



*APA – The Engineered Wood Association* is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by International Code Council (ICC) International Accreditation Service (IAS), and an accredited testing organization under ISO/IEC 17025 by IAS. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, and Validation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

**APA – THE ENGINEERED WOOD ASSOCIATION  
HEADQUARTERS**

7011 So. 19<sup>th</sup> St. ▪ Tacoma, Washington 98466  
Phone: (253) 565-6600 ▪ Fax: (253) 565-7265 ▪ Internet Address: [www.apawood.org](http://www.apawood.org)

**PRODUCT SUPPORT HELP DESK**  
(253) 620-7400 ▪ E-mail Address: [help@apawood.org](mailto:help@apawood.org)

**DISCLAIMER**

APA Product Report® is a trademark of *APA – The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.